

**Jobling Purser Ltd**

Paradise Works  
Scotswood Road  
Newcastle-upon-Tyne NE4 8NY  
Tel: 0191-273 2331 Fax: 0191-226 0129  
e-mail: info@joblingpurser.com  
website: www.rocbinda.com

12 Y

**H A P A S**

**Roads and Bridges  
Agrément Certificate  
No 99/H031**

Second issue\*

Designated by Government  
to issue  
European Technical  
Approvals

## ROCBINDA/COLORVIAL HIGH-FRICTION SURFACING SYSTEM

This Certificate is issued under the Highway Authorities Product Approval Scheme (HAPAS) by the BBA in conjunction with the Highways Agency (acting on behalf of the overseeing organisations of the Department for Transport; the Scottish Executive Development Department; the Welsh Assembly Government; the Department for Regional Development, Northern Ireland), the CSS (formerly the County Surveyors' Society), the Local Government Technical Advisers Group, and industry bodies. HAPAS Agrément Certificates are normally each subject to a review every five years.

## Product



• THIS CERTIFICATE RELATES TO THE ROCBINDA/COLORVIAL HIGH-FRICTION SURFACING SYSTEM, COMPRISING A TWO-COMPONENT POLYURETHANE BINDER AND A GRADED (1 mm TO 3 mm) CALCINED BAUXITE AGGREGATE.

• The system is for use as a high-friction surfacing on highways with bituminous or concrete surfaces and is classified as Type 1 in accordance with the Guidelines Document for the Assessment and Certification of High-Friction Surfaces for Highways.

• The system is marketed in the UK as Rocbinda and installed only by BBA Approved Installers.

• The system is also marketed outside the UK as Colorvial by ColorVial SL, GranVia 630, 4a planta, 08007 Barcelona, Spain.  
Tel: +34 93 270 2880, Fax: +34 93 412 7124.  
e-mail: info@colorvial.com,  
website: www.colorvial.com

## HAPAS Requirements

### 1 Requirements

1.1 The Highways Technical Advisory Committee (HiTAC) and HAPAS Specialist Group 1 (High-Friction Surfacing) have agreed with the British Board of Agrément the aspects of performance to be used by the BBA in assessing the compliance of high-friction surfacing systems with the Guidelines Document. In the opinion of the BBA, the Rocbinda/Colorvial High-Friction Surfacing System, when applied to suitable bituminous or concrete surfaces, in accordance with the provisions of this Certificate, will meet the relevant requirements and is deemed to be of Type 1.

1.2 Additional requirements of the overseeing organisations are given in the Manual of Contract Documents for Highway Works, Volume 1 (MCHW 1) Specification for Highway Works, Series 900.

## Regulations

### 2 Construction (Design and Management) Regulations 1994 (as amended)

#### Construction (Design and Management) Regulations (Northern Ireland) 1995 (as amended)

Information in this Certificate may assist the client, planning supervisor, designer and contractors to address their obligations under these Regulations.

See sections: 5 *Delivery and site handling* (5.1 and 5.2); 7 *Precautions during installation*.

## Technical Specification

### 3 Description

3.1 The Rocbinda/Colorvial High-Friction Surfacing System comprises a two-component polyurethane binder and a graded (1 mm to 3 mm) calcined bauxite aggregate.

3.2 Rocbinda/Colorvial concrete primer is available for use on concrete surfaces prior to the application of the system.

3.3 The system is available in standard, summer and winter grades. The winter grade may be used where ambient temperatures are between 5°C and 15°C.

### 4 Manufacture and quality control

The binder components are manufactured by a batch-blending process. A series of quality control checks is conducted on each batch. The combinations tested are identified by batch numbers which are recorded on a Certificate of Conformity prior to delivery to site.

### 5 Delivery and site handling

5.1 The product is delivered to site in 16 kg or 8 kg packs. The activator is supplied in a metal container and the base in a plastic container.

5.2 The components are classified under the Chemicals (Hazard Information and Packaging for Supply) Regulations 2002 (CHIP3) and all containers bear the appropriate hazard warning label(s). Flashpoints and hazard classifications are given in Table 1.

Table 1 Flashpoint and hazard classification

Component	Flashpoint (°C) <sup>(1)</sup>	Classification
Base	>200	Not hazardous
Activator	>200	Harmful by inhalation
Primer	50	Harmful by inhalation

(1) Closed cup.

5.3 When stored in accordance with the Certificate holder's instructions the unopened components have a shelf-life of at least 12 months.

## Design Data

### 6 General

6.1 The Rocbinda/Colorvial High-Friction Surfacing System is satisfactory for use as a high-friction surfacing on highways with bituminous or concrete surfaces with surface texture depths of between 0.5 mm and 3.0 mm, measured using the sand patch test as defined in BS 598-105 : 1990.

6.2 The system is classified as Type 1, in accordance with the results of the performance tests as defined in Table 1 of the Guidelines Document for the Assessment and Certification of High-Friction Surfaces for Highways.

6.3 Installation of the system should be carried out only when the road surface temperature is between 5°C and 35°C.

6.4 Concrete surfaces must be primed with Rocbinda/Colorvial concrete primer prior to the application of the system.

6.5 The in-service colour retention has not been assessed and is outside the scope of this Certificate.

### 7 Precautions during installation

Health and Safety Data Sheets and COSHH risk assessments for the works should be deposited with the purchaser and be maintained on site.

### 8 Maintenance and repair

Should the system be damaged or become debonded from the substrate, it may be repaired by cutting the damaged area back to firmly bonded material, squaring off the area to be reinstated, cleaning the prepared area, masking the perimeter and reinstating to the original specification. A 50 mm overlap onto the existing material should be allowed.

### 9 Durability

9.1 The results of the performance tests and the performance of the system in use, indicate that when used in an appropriate location, as defined in the Guidelines Document for the Assessment and Certification of High-Friction Surfaces for Highways, the system should have a service life of between 5 and 10 years (see Table 2).

Table 2 Area<sup>(1)</sup> of application by type classification

Site category (as defined in HD28/94)	Site definition	Maximum traffic levels (number of commercial vehicles per lane per day)		
		Type 1	Type 2	Type 3
F	Approaches to and across major junctions (all limbs)	3500	1000	250
G1	Gradient — from 5% to 10%, longer than 50 m			
H1	Bend — not subject to 40 mph or lower speed limit, radius from 100 m to 250 m			
L	Roundabout			
G2	Gradient — >10%, longer than 50 m	2500	750	175
H2	Bend — not subject to 40 mph or lower speed limit, radius <100 m			
J/K	Approach to hazard, such as roundabout, traffic signals, pedestrian crossing, railway level crossing	2500	500	100

(1) Suitable areas for use of systems classified in accordance with Table 1 of the Guidelines Document to give an expected service life of 5 to 10 years.

9.2 If the system is used in other locations or exposed to different traffic levels, the expected life will be increased or decreased in relation to the severity of the site.

## Installation

### 10 General

10.1 Installation of the Rocbinda/Colorvial High-Friction Surfacing System is carried out only by BBA Approved Installers.

10.2 The Certificate holder is responsible for training and monitoring the BBA Approved Installers to ensure the system is installed in accordance with the BBA agreed Method Statement and this Certificate.

### 11 Preparation

11.1 Any imperfections in the road surface not acceptable to the installer should be reinstated with a material approved by the purchaser in consultation with the installer.

11.2 The installer should ensure that the road surface is clean, dry, and free from ice, frost, loose aggregate, oil, grease, road salt and other loose matter likely to impair adhesion of the system to the road surfacing.

11.3 The ambient and road surface temperatures should be recorded. Installation should not be carried out if the road surface temperature is outside the range of 5°C to 35°C.

11.4 If ambient temperature is between 5°C and 15°C, then the winter grade system could be used.

### 12 Application

12.1 The activator is added to the base component and mixed for at least two minutes or until homogeneous, using a high-torque drill fitted with a helical mixing blade.

12.2 The mixed binder is spread onto the prepared surface with a squeegee at a minimum coverage rate, which will vary according to the texture and porosity of the surface but shall not be less than 1.35 kgm<sup>-2</sup>.

12.3 After the binder is applied an excess of calcined bauxite aggregate is broadcast over the binder and is spread out evenly using a broom or squeegee.

12.4 After the binder is sufficiently cured, the excess aggregate is removed by vacuum sweeper or other suitable means.

12.5 Rolling of the aggregate is not permitted.

### 13 Aftercare

The installer should carry out a visual check on the installation for uniform surface texture, surface blemishes and any discernible faults. Any remedial work is conducted as necessary.

## Technical Investigations

The following is a summary of the technical investigations carried out on the Rocbinda/Colorvial High-Friction Surfacing System.

### 14 Tests

Laboratory performance tests were carried out on the system (see Tables 3 and 4).

**Table 3** Laboratory performance tests on asphalt substrates

Test		Parameter	Method in TRL Report 176 <sup>(1)</sup>	Type 1 requirement
Scuffing at 45°C	Initially	Texture depth (mm)	Appendix G	≥1.4
	After 500 wheel-passes	Texture depth (mm)	Appendix G	≥1.2
		Erosion index		≤3
	After heat ageing for 112 days at 70±3°C and 500 wheel-passes	Texture depth (mm)	Appendix G	≥1.2
		Erosion index		≤5
	Wear	Initially	Texture depth (mm)	Appendix H
		SRV		≥65
After 100,000 wheel-passes		Texture depth (mm)	Appendix H	≥1.1
		Erosion index		≤3
		SRV		≥70
Tensile adhesion			Stress at -10±2°C (Nmm <sup>-2</sup> )	Appendix J
		Stress at 20±2°C (Nmm <sup>-2</sup> )	Appendix J	≥0.5

(1) Including any agreed amendments detailed in Appendix D of the Guidelines Document for the Assessment and Certification of High-Friction Surfaces for Highways.

**Table 4** Additional tests

Test	Parameter	Method in TRL Report 176 <sup>(1)</sup>	Result
Resistance to freeze/thaw	Texture depth Erosion index	Appendix L	satisfactory
Resistance to diesel	Texture depth Erosion index	Appendix M	satisfactory
Thermal movement	Thermal expansion coefficient	Appendix N	satisfactory
Concrete substrate test	Texture depth Erosion index Tensile adhesion at 20±2°C	Appendix P	satisfactory

(1) Including any agreed amendments detailed in Appendix D of the Guidelines Document for the Assessment and Certification of High-Friction Surfaces for Highways.

### 15 Investigations

15.1 An installation trial was carried out to assess the practicability of the installation and quality control/assurance procedures.

15.2 A user/specifier survey relating to existing sites, at least two years old, was carried out to assess the system's performance and durability.

15.3 The manufacturing process was examined, including the methods adopted for quality control, and details were obtained of the quality and composition of materials used.

## Bibliography

BS 598-105 : 1990 *Sampling and examination of bituminous mixtures for roads and other paved areas — Methods of test for the determination of texture depth*

*Guidelines Document for the Assessment and Certification of High-Friction Surfaces for Highways*

TRL Report 176 : 1997 *Laboratory tests on high-friction surfaces for highways*

HD 28/94 *Design Manual for Roads and Bridges : Volume 7, Pavement Design and Maintenance : Skid Resistance*

Manual of Contract Documents for Highway Works, Volume 1 : *Specification for Highway Works* : May 2001 edition

## Conditions of Certification

### 16 Conditions

16.1 This Certificate:

- (a) relates only to the product that is described, installed, used and maintained as set out in this Certificate;
- (b) is granted only to the company, firm or person identified on the front cover — no other company, firm or person may hold or claim any entitlement to this Certificate;
- (c) is valid only within the UK;
- (d) has to be read, considered and used as a whole document — it may be misleading and will be incomplete to be selective;
- (e) is copyright of the BBA;
- (f) is subject to English law.

16.2 References in this Certificate to any Act of Parliament, Regulation made thereunder, Directive or Regulation of the European Union, Statutory Instrument, Code of Practice, British Standard, manufacturers' instructions or similar publication, are

references to such publication in the form in which it was current at the date of this Certificate.

16.3 This Certificate will remain valid for an unlimited period provided that the product and the manufacture and/or fabrication including all related and relevant processes thereof:

- (a) are maintained at or above the levels which have been assessed and found to be satisfactory by the BBA;
- (b) continue to be checked as and when deemed appropriate by the BBA under arrangements that it will determine;
- (c) are reviewed by the BBA as and when it considers appropriate; and
- (d) remain in accordance with the requirements of the Highway Authorities Product Approval Scheme.

16.4 In granting this Certificate, the BBA is not responsible for:

- (a) the presence or absence of any patent or similar rights subsisting in the product or any other product;
- (b) the right of the Certificate holder to market, supply, install or maintain the product; and
- (c) the nature or standard of individual installations of the product or any maintenance thereto, including methods and workmanship.

16.5 Any recommendations relating to the use or installation of this product which are contained or referred to in this Certificate are the minimum standards required to be met when the product is used. They do not purport in any way to restate the requirements of the Health & Safety at Work etc Act 1974, or of any other statutory, common law or other duty which may exist at the date of this Certificate or in the future; nor is conformity with such recommendations to be taken as satisfying the requirements of the 1974 Act or of any present or future statutory, common law or other duty of care. In granting this Certificate, the BBA does not accept responsibility to any person or body for any loss or damage, including personal injury, arising as a direct or indirect result of the installation and use of this product.



In the opinion of the British Board of Agrément, the Rocbinda/Colorvial High-Friction Surfacing System is fit for its intended use provided it is installed, used and maintained as set out in this Certificate. Certificate No 99/H031 is accordingly awarded to Jobling Purser Ltd.

On behalf of the British Board of Agrément

Date of Second issue: 18th February 2004

  
Chief Executive

\*Original Certificate issued 24th June 1999. This amended version includes reference to an additional system name and associated marketing company's name for use outside the UK and revised Conditions of Certification.

British Board of Agrément

P O Box No 195, Bucknalls Lane  
Garston, Watford, Herts WD25 9BA  
Fax: 01923 665301

©2004

e-mail: mail@bba.star.co.uk  
website: www.bbacerts.co.uk



For technical or additional information, contact the Certificate holder (see front page).  
For information about the Agrément Certificate, including validity and scope, tel: Hotline 01923 665400, or check the BBA website.